

# 615

## HTG #2

### APPLICATION AREAS

- All types of anti-friction bearings, roller bearings and ball bearings
  - Conveyors
  - Grinding Mills
  - Blowers
  - Crushers
- Mechanical Presses
- Cranes/Guides/Slides



### PRODUCT DATA SHEET

#### KEY FEATURES AND BENEFITS

- Superior resistance to water washout
- Exceptional shear resistance
- Compatible with most greases
- NSF H2 - Registration number 133940
- Contains no toxic heavy metals
- Excellent for extremes in pressure and temperature

#### PACKAGING

400g  
18kg  
55kg  
180kg

#### DIRECTIONS

Apply with a grease gun, or brush on for local applications. Before using, wipe grease fittings to remove contamination. Keep grease container closed when not in use. Reapply at regular intervals.

#### DESCRIPTION

Chesterton® 615 HTG #2 is the one grease to use for the most demanding of lubrication needs. It is a multi-purpose workhorse with outstanding extreme pressure capabilities. With a temperature limit of 204°C, it performs at temperatures well beyond that of most conventional petroleum greases. The product is compatible with most other popular greases, has outstanding shear resistance and excellent corrosion resistance. Even when up to 50% water is incorporated into the product, the grease maintains its protective film and can withstand extremes of pressure. Uses for Chesterton 615 HTG #2 can be found throughout any industrial plant. It is especially advantageous where there is a high water environment such as in a pulp and paper mill, extremes of pressure such as in mining operations, or extremes of temperature such as in steel mills.

#### TYPICAL PHYSICAL PROPERTIES

Appearance	Blue-Green
Consistency, NLGI	2
Texture	Buttery with slight tack
Specific Gravity	0.97
Dropping Point (ASTM D 566, DIN 51 801/1)	318°C (604°F)
Penetration (ASTM D 217, DIN ISO 2137)	265-295
Timken OK Load (ASTM D 2509)	29.5 kg (65 lbs)
Four Ball Wear Test (ASTM D 2266, DIN 51 350/5) Scar Diameter	0,4 mm
Four Ball Wear Test (ASTM D 2596, DIN 51 350/4) Weld Load Wear Index	620 kg (1364 lbs) 85
Operating Temperature (above 170°C, increased lubrication frequency is required)	-40°C (-40°F) to 204°C (400°F)
Shear Stability (ASTM D 217), % Change 10,000 strokes 100,000 strokes	+2% +4%
Oil Separation (ASTM D 1742), % loss	0.2%
Wheel Bearing Life (ASTM D 3527)	120 hrs
Water Washout (ASTM D 1264)	< 0.05%
Corrosion Resistance (ASTM B 117), 5% NaCl	>1000 hrs @ 50 micron film thickness
Base Oil Viscosity (ASTM 445) @ 40°C	100 cSt

Before using this product, please refer to Safety Data Sheet (SDS).