



LS2966/20

NLGI 1.5

Applications

--

Features and Benefits

--

Typical Characteristics

Appearance	Visual	Smooth
Colour	Visual	Beige
Thickener Type		Complex
Temperature Range		-30°C to 120°C (-4°F - 248°F)
Worked Penetration	IP 50	290—320
Drop Point	IP 396	170°C
Oil Separation (40°C, 168hrs)	IP 121	<5%
4-Ball Wear Scar	IP 239	0.6mm
4-Ball Weld Load	IP 239	620kg
Emcor Corrosion (distilled water)	IP 220	0,0
Copper Corrosion (100°C, 24hrs)	IP 122	1a
Water Wash Out	ASTM D1264	5%

Base Oil Characteristics

Type		Mineral
Kinematic Viscosity (40°C)	ASTM D445	100cSt
Flash Point	IP 34	>220°C