

**Specialty
Lubricants**

**MOLYKOTE® G 67
Extreme pressure grease**

FEATURES

- Excellent protection against fretting corrosion
- Good load carrying capacity
- High level of protection against wear
- Particularly adhesive

COMPOSITION

- Mineral oil
- Lithium soap
- Adhesion improver
- Solid lubricants

APPLICATION

- Spur gear systems, load chains, settling shims, springs, shaft-hub connection, encapsulated joints, gears, linear motion guides.

TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Standard*	Test	Unit	Result
	Color		Beige
	Penetration, density, viscosity		
DIN 51 818	NLGI consistency class		1
ISO 2137	Worked penetration	mm/10	310-340
ISO 2811	Density at 20°C	g/ml	1.12
DIN 51 562	Base oil viscosity at 40°C	mm ² /s	115
	Temperature		
	Service temperature	°C	-25 to +120
ISO 2176	Drop point	°C	155
	Load-carrying capacity, wear protection, service life		
	Four-ball tester (VKA)		
DIN 51 350 T.4	Weld load	N	4800
DIN 51 350 T.5	Wear scar under 600N load	mm	0.75
	Almen-Wieland machine, OK load	N	20000
	Fretting corrosion - Deyber tester		>36x10 ⁴
	Resistance		
DIN 51 808	Oxidation resistance, pressure drop 100h, 99°C	bar	2.5
	Corrosion protection		
DIN 51 802	Emcor method		0-1
	Coefficient of friction		
	Steel ball against plastic surface (POM)		
	Ø ball = 12.7mm, load = 6.3N, v = 10mm/s, 24h	µ	0.08
	Oil separation - evaporation		
DIN 51 817	Oil separation - standard test	%	4.3
Fed-Standard 791-32-2	7 days, 40°C		

* ISO: International Standardisation Organisation
DIN: Deutsche Industrie Norm

HOW TO USE

How to apply

Clean points of contact. Apply in same way as lubricating greases, using brush, spatula, grease-gun or automatic lubricating device. Suitable for delivery by central lubricating system. In the event of long breaks in service e.g. overnight, the pressure in the delivery equipment should be relieved. Not to be mixed with other greases.

Because of variation in quality of plastics and elastomers, compatibility tests should be carried out for swelling and shrinkage, stress-crack formation, and changes in strength and hardness.

HANDLING PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE FROM YOUR LOCAL DOW CORNING SALES REPRESENTATIVE.

USABLE LIFE AND STORAGE

When stored at or below 20°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

PACKAGING

This product is available in 1kg cans, 400g cartridges and 5kg drums.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Health,

Environment and Regulatory Affairs specialists available in each area.

For further information, please consult your local Dow Corning representative.

WARRANTY INFORMATION - PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Dow Corning specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless Dow Corning provides you with a specific, duly signed endorsement of fitness for use, Dow Corning disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.