

# ***Molykote*<sup>®</sup> P-40 Metal-Free Adhesive Lubricating Paste**

## **FEATURES & BENEFITS**

- Excellent adhesion
- Good corrosion protection
- Good water resistance
- Good antifretting
- Assembly and continuous lubrication
- Metal-free
- Low water pollution class

Metal-free adhesive lubrication paste

## **APPLICATIONS**

- Assembly and threaded connections, spline shafts, mounting of bearings.
- Continuous lubrication for:
  - Various parts in brake systems, in brake rods, guide bolts
  - Axles of commercial vehicles, cams and plain bearings
  - Open Gears
  - Marine applications

## **TYPICAL PROPERTIES**

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

<b>Test*</b>	<b>Property</b>	<b>Unit</b>	<b>Result</b>
	Color		Yellowish Brown
	<b>Consistency, viscosity</b>		
ISO 2137	Unworked penetration	mm/10	310 - 350
DIN 51 562	Base oil viscosity at 40°C (104°F)	mm <sup>2</sup> /s	400
	<b>Temperature</b>		
	Service temperature range		
	- as paste	°C	-40 to +121
		°F	-40 to +250
	- solid lubricants	°C	-40 to +1093
		°F	-40 to +2000
	Deutsche Bahn AG test		
	- stirrability at -35°C (-31°F)		4
DIN 51 805	Kestemich method - flow pressure at -30°C (-22°F)	mbar	360
DIN 2176	Dropping point	°C	None
		°F	None
	<b>Load-carrying capacity, wear protection, service life</b>		
	Four-ball tester (VKA)		
DIN 51 350 pt.4	Weld load	N	3000
DIN 51 350 pt.5	Wear scar under 800N load	mm	0.94
	Fretting corrosion – Deyber tester		25 x 10 <sup>6</sup>
	<b>Coefficient of friction</b>		
	Press-Fit test, $\mu =$		0.09
	Screw test - $\mu$ thread <sup>1</sup>		0.16
	Screw test - $\mu$ head <sup>1</sup>		0.08
SRV Optimal	Oscillating endurance test, $\mu =$ <sup>2</sup>		0.13

## TYPICAL PROPERTIES (continued)

Test	Property	Unit	Result
	<b>Corrosion protection</b>		
DIN 51 802	SKF-Emcor method-degree of corrosion		0
	Salt spray test	h	500

\*ISO: International Standardization Organization.

DIN: Deutsche Industrie Norm.

<sup>1</sup>Coefficient of friction in bolted connection, M12 x 1.75, material 8.8, blackened.

<sup>2</sup>Load: 300N, frequency: 50Hz, amplitude: 0.5mm, 2h.

### DESCRIPTION

*Molykote*<sup>®</sup> P-40 is a metal-free adhesive lubrication paste which can be used for all assembly and continuous lubricating jobs, particularly those exposed to corrosive environments such as splash water or humidity.

### HOW TO USE

#### How to apply

The sliding surfaces should be cleaned. The paste should then be applied with a suitable brush, rag or grease gun. It should not be mixed with greases or oils.

### HANDLING

#### PRECAUTIONS

#### PRODUCT SAFETY

**INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT DOW CORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.**

### USABLE LIFE AND STORAGE

When stored at or below 20°C (68°F) in the original unopened containers, this product has a usable life of 60 months from the date of production.

### PACKAGING INFORMATION

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest Dow Corning sales office or Dow Corning distributor.

### LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

### HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, [dowcorning.com](http://dowcorning.com) or consult your local Dow Corning representative.

### LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

*We help you invent the future.*<sup>™</sup>

[molykote.com](http://molykote.com)